

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
1 July 2004 (01.07.2004)

PCT

(10) International Publication Number
WO 2004/055109 A2

(51) International Patent Classification⁷: **C08L 77/00**

(21) International Application Number:
PCT/NL2003/000873

(22) International Filing Date:
10 December 2003 (10.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02080263.3 16 December 2002 (16.12.2002) EP

(71) Applicant (for all designated States except US): **DSM IP ASSETS B.V. [NL/NL]**; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **OTTENHEIJM, Johannes, Hendrikus, Godefriedus [NL/NL]**; Heerottostraat 28, NL-6121 NA Born (NL).

(74) Agent: **KRIJGSMAN, W.**; DSM Intellectual Property, P.O. Box 9, NL-6160 MA Geleen (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 2004/055109 A2

(54) Title: PROCESS FOR PREPARING A FLAME RETARDANT POLYAMIDE COMPOUND

(57) **Abstract:** The invention relates to a process for preparing a flame retardant polyamide compound comprising melt-mixing of a composition comprising at least a polyamide polymer having a weight-average molecular weight of at least 10,000 g/mol, an amount of 1-100 wt.% relative to the total weight of polyamide of a flame retardant, and an amount of 0.1-30 wt.%, relative to the total weight of polyamide, of a polyamide oligomer having a weight-average molecular weight of at most 7,500 g/mol.